

HLB GROUP TECHNICAL SPECIFICATIONS

UNIT	DENSITY			INDENTATION HARDNESS AT 40%			COMPRESSION SET		ELONGATION AT BREAK			TEAR STRENGTH		RESILIENCE		
	TS EN ISO 845			TS EN ISO 2439			TS EN ISO 1856		TS EN ISO 1798			ASTIM D3574-F		TSE EN ISO 8307		
	KG / M3			N			%		%			N / CM		%		
	±	MIN.	MAX.	± %15	MIN.	MAX.	NOMİNAL	MAX.	±%50	MIN.	MAX.	≥	MAX.	± 5	MIN.	MAX.
45 HLB	±2	43,00	47,00	350	298	403	3	4,00	90	40,00	140,00	2,6	2	40	35,00	45,00