

FLEXSOFT GROUP TECHNICAL SPECIFICATIONS

UNIT	DENSITY			INDENTATION HARDNESS AT 40%			COMPRESSION SET		ELONGATION AT BREAK			TEAR STRENGTH		RESILIENCE		
	TS EN ISO 845			TS EN ISO 2439			TS EN ISO 1856		TS EN ISO 1798			ASTIM D3574-F		TSE EN ISO 8307		
	KG / M3			N			%		%			N / CM		%		
	±	MIN.	MAX.	± %15	MIN.	MAX.	NOMINAL	MAX.	±%50	MIN.	MAX.	≥	MAX.	± 5	MIN.	MAX.
32 D FLEXSOFT	±1,5	30,50	33,50	210	179	242	2,17	4,00	155	105,00	205,00	3,16	2,5	50	45,00	55,00
35 D FLEXSOFT	±1,5	33,50	36,50	230	196	265	2,48	4,00	130	80,00	180,00	2,7	2,5	50	45,00	55,00