

FLAME LAMINATION GROUP TECHNICAL SPECIFICATIONS

UNIT	DENSITY			INDENTATION HARDNESS AT 40%			COMPRESSION SET		ELONGATION AT BREAK			TEAR STRENGTH		RESILIENCE		
	TS EN ISO 845			TS EN ISO 2439			TS EN ISO 1856		TS EN ISO 1798			ASTIM D3574-F		TSE EN ISO 8307		
	KG / M3			N			%		%			N / CM		%		
	±	MIN.	MAX.	± %15	MIN.	MAX.	NOMİNAL	MAX.	± %50	MIN.	MAX.	≥	MAX.	± 5	MIN.	MAX.
24 D ALEV	±1,5	22,50	25,50	150	128	173	11,30	14,00	230	180,00	280,00	4,64	3	35	30,00	40,00
26 D ALEV	±1,5	24,50	27,50	160	136	184	7,45	12,00	220	205,00	305,00	5,45	3	35	30,00	40,00
30 D ALEV	±1,5	28,50	31,50	170	145	196	4,38	12,00	210	160,00	260,00	5,14	3	35	30,00	40,00
32 D ALEV	±1,5	30,50	33,50	170	145	196	4,30	12,00	200	150,00	250,00	5,2	3	35	30,00	40,00