

VISCO GROUP TECHNICAL SPECIFICATIONS

UNIT	DENSITY			INDENTATION HARDNESS AT 40%			COMPRESSION SET		ELONGATION AT BREAK			TEAR STRENGTH		RESILIENCE		
	TS EN ISO 845			TS EN ISO 2439			TS EN ISO 1856		TS EN ISO 1798			ASTIM D3574-F		TSE EN ISO 8307		
	KG / M3			N			%		%			N / CM		%		
	±	MIN.	MAX.	± %15	MIN.	MAX.	NOMINAL	MAX.	± %50	MIN.	MAX.	≥	MAX.	± 5	MIN.	MAX.
30 D VISCO	±2	28,00	32,00		60	51	69	1,3		3,00	170	120,00	220,00	1,3		1
40 D VISCO	±2	38,00	42,00		60	51	69	1,3		3,00	170	120,00	220,00	1,3		1
50 D VISCO	±2	48,00	52,00		60	51	69	1,3		3,00	170	120,00	220,00	1,3		1
50 D VISCO SOLE	±3	57,00	63,00		280	238	322	1,73		5,00	110	60,00	160,00	4,22		1